

non-animal origin

rheological additive

for cosmetics and toiletries

GENERAL INFORMATION

EA-3105 is a specially prepared dispersion of an organically modified hectorite in volatile silicone (pentamer).

This grade is designed to impart rheological control and suspension to organic- and silicone-based cosmetics.

EA-3105 is also particularly useful in emulsions and can be used in "cold process" systems. It provides thermostable viscosity control of the emulsion's oil phase, improves application properties, enhances skin-feel by masking greasy or tacky components and imparts a pleasant residual silkiness to the skin.

EA-3105 is an alternative to traditional polymer or cellulose-based thickeners for stabilising emulsions.

INGREDIENTS**INCI name:**

Cyclopentasiloxane, Disteardimonium Hectorite, Triethyl Citrate

APPLICATIONS

- Antiperspirants
- Eye Make-Up
- Emulsions
- Creams and Lotions
- Sun Care Products

KEY PROPERTIES**EA-3105 rheological additive****Non-animal origin****Rheological control**

- Predictable, reproducible and stable viscosity control
- Shear-thinning viscosity
- Excellent suspension of pigments and actives
- Controlled alignment of special-effect pigments
- Thermostable viscosity raises apparent melting point and ensures cost-efficient use of UV filters
- Emulsion stabilization [w/o and o/w]

Convenience

- Optimally pre-activated and dispersed organoclay
- Incorporates with medium-shear mixing
- Can be added at any convenient stage of manufacture
- Gives a high degree of formulating flexibility
- Provides highly reproducible results for multi-site production requirements

Acceptability

- Non-abrasive
- Provides smooth feel to skin
- Toxicologically safe ingredients

CHEMICAL AND PHYSICAL DATA

Color / Form	Light Buff
Viscosity, Brookfield Helipath, TF spindle, mm cps @ 2.5 rpm	2.5 – 6.5
% Ash Content	10.8 – 11.8
Infrared	To Match Standard
Microbial Content	Less than 100 cfu/g

"Note: Microbial results are based on analysis of irradiated organoclay prior to gel formulation."

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2018, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

INCORPORATION

EA-3105 can be added at any convenient suitable stage during the manufacturing cycle. The additive is a very high viscosity, shear-thinning product. To ensure good homogeneous mixing is achieved, care must be taken to overcome the large viscosity differential existing between the EA-3105 and the other lower viscosity components. Choice of mixing equipment and the configuration within the mixing vessels are critical factors in developing the optimum performance of the EA-3105 additives. The use of medium- to high-shear mixing equipment is recommended.

Batch Processing

Single Phase Systems

Always add EA-3105, under shear, to a portion of the organic component or solvent with which it is most compatible. Mix until homogeneous before adding the other ingredients.

Multi-Phase Systems e.g. emulsions

Treat as the single phase but always ensure the additive is thoroughly mixed in before the emulsification stage.

Continuous Processing

EA-3105 should be added to the oil phase at any convenient point that meets the above guidelines for batch processing. In multi-manifold systems, a flowable pre-mix of EA-3105 with a compatible oil or solvent should be made in a side pot.

Where only lower-shear mixing equipment is available, stir EA-3105 alone and then slowly add the most compatible component by portions, always ensuring the mixture remains homogeneous at each stage.

LEVELS OF USE

The level of use of EA-3105 will depend on the formulation. Suspension will be provided by 2.5-10.0% additions. In emulsions, thickening will occur in the oil phase only and emulsion viscosities will be influenced by 3-5% additions. Novel emulsification effects can be achieved,

giving light feel and lower viscosities. In some water-in-oil systems a reduction of surfactant may be achievable by the use of EA-3105.

Higher levels of EA-3105 will have a greater viscosity influence and thermostable viscosity in single phase systems may be achieved by 10-25% additions.

COMPATIBILITY

The gel additives can contribute greatly to a formulation's stability by improving the compatibility of other ingredients. Care should be taken to determine the compatibility of the additive with the oils, actives or surfactant ingredients within a formulation. The wide range of grades available allows selection of the optimal carrier and organoclay for each system.

TOXICITY

Care is taken to ensure that the ingredients used in gel additives are not known to be injurious to health in any way and have been toxicologically tested to ensure their safety. However, the gel additives have not been subjected to testing involving the use of animals within the last 10 years.

STORAGE TEMPERATURES

This product contains cyclopentasiloxane. Store away from excessive heat.

SHELF LIFE

EA-3105 has a minimum shelf life of 2 (two) years from date of manufacture.

SAFETY

Before using this product, please consult our MSDS.

USA Head Office

Elementis Specialties, Inc.
469 Old Trenton Road
East Windsor, NJ 08512
USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis UK Ltd
c/o Elementis GmbH
Stolberger Strasse 370
50933 Cologne
Germany
Tel.: +49 221 2923 2000
Fax: +49 221 2923 2011

Malaysia

Elementis Specialties, Inc.
Lot PT 55, 64 & 65
Jalan Hulu Tinggi 26/6
Seksyen 26
40400 Shah Alam
Selangor Darul Ehsan
Malaysia
Tel.: +60 3 5191 9979
Fax: +60 3 5191 6811

China

Deuchem (Shanghai) Chemical Co., Ltd.
99, Liyang Road
Songjiang Industrial Zone
Shanghai
China 201613
Tel.: +86 21 5774 0348
Fax: +86 21 5774 3563